



Descrizione

Giuntura a base di fibre minerali sintetiche ad alta tenacità e leganti elastomerici (NBR). Le prestazioni sono garantite fino ad una temperatura massima di 200°C e ad una pressione massima di 60 bar. La guarnizione è di colore verde con uno spessore da 0,5 a 5 mm.

Applicazioni

Tenuta a contatto con acqua, aria, azoto, olii.

Parametri	Certificazioni	Valori	U.m.		
			s.mm 1,5/2	s.mm. 3	U.m.
Densità » g/cm3	DIN 3754	1,8			
temperatura massima per brevi esposizioni » °C	-	180			
temperatura per esercizio in continuo anche con fluidi ossidanti » °C	-	-20 +140			
Pressione massima di esercizio » bar	-	40			
Compressibilità » %	ASTM F36J	8			
Ritorno elastico minimo » %	ASTM F36J	45			
Stress Retention 16 ore a 175 °C 50 » N/mm2	DIN 52913	20			
Resistenza alla trazione (trasversale) » N/mm2	DIN 52910	7			
Perdita alla calcinazione » %	DN 52911	30			
Permeabilità all'azoto » mg/s.m	DIN 3535/4	0,05			
Immersione in olio ASTM B per 5 ore a 23 °C					
Aumento di peso » %	ASTM F146	10			
Aumento di spessore » %	ASTM F146	10			





Description

Joint based on synthetic mineral fibers with high toughness and elastomeric binders (NBR). The performance is guaranteed up to a maximum temperature of 200 ° C and a maximum pressure of 60 bar.
The gasket is green with a thickness of 0.5 to 5 mm.

Applications

Holding in contact with water, air, nitrogen, oils.

Parameters	Method	Values	U.m.		
			s.mm 1,5/2	s.mm. 3	N/ mm ²
Density	DIN 3754	1,8			
Max temperature for short exposures » °C	-	180	y	25,5	11,05
Temperature for continuous operation even with oxidizing fluids » °C	-	-20 +140	m	2,75	2
Maximum operational pressure » bar	-	40			
Compressibility » %	ASTM F36J	8			
Minimum springback » %	ASTM F36J	45			
Stress Retention 16 hours at 175 °C 50 » N/mm ²	DIN 52913	20			
Tensile strength (transverse) » N/mm ²	DIN 52910	7			
Loss on calcination » %	DIN 52911	30			
Nitrogen permeability » ml/min	DIN 3535/4	0,05			
Immersion in ASTM IRM 903 for 5 hours at 150°C					
Weight increase » %	ASTM F146	10			
Thickness increase » %	ASTM F146	10			

The graph shows a downward-sloping curve representing the stress retention of the gasket over a range of pressures from 0 to 50 bar. The vertical axis is labeled 'Pressione (bar)' and ranges from 0 to 200. The horizontal axis is labeled 'Pressione (bar)' and ranges from 0 to 50. A shaded area under the curve indicates the pressure range where the gasket maintains its strength.

Pressione (bar)	Pressione (bar)	Pressione (bar)
0	180	25,5
10	140	11,05
20	120	—
30	100	—
40	80	—
50	60	—

